

FOSHEE





CREPIM

e par Actions Simplifiee -792 178 816 R.C.S. ARRAS clai: Parc de la Porte Nord - nas Christophe Coloni 62700 BRUAY LA BUISSERE France Tél: 03.21.61.64.00 Fax: 03.21.61.64.01 E-mail: contact@usepim.fr www.crepim.fr SRET 792 178 816 00015 / APE 71128 / T.V.A. 6685 792 178 818

Autrement dit / In other words, A1

Classement de réaction au feu / Reaction to fire classification:

A1

4.3 Champ d'application / Field of application:

Le présent classement est valable pour les paramètres suivants liés au produit / The classification is valid for the following product parameters:

Composition: Aucune variation autorisée / No variation allowed

Epaisseur / Thickness: 1.25 mm

Masse surfacique / Surface density: 1.22 kg/m2

Couleur / Color: Sable / Sandy

Le classement est valable pour les conditions d'utilisation finale suivantes / The classification is valid for the following end-use condition:

Support / Substrate: Sans substrat / Without substrate. Fixation / Mounting method: Sans fixation / Without fixation.

5. Restrictions / Limitations

Le présent document de classement ne constitue ni une approbation de type ni une certification du produit.

This classification document does not represent type of approval or certification of the product.

Signé

Signature de la personne qui effectue le classement Signature of the person who realize the classification

Thomas TURF Ingénieur praticien Test engineer

Approuvé

signature de la personne autorisant le présent rapport Signature of the person who authorize the report

Skander KHELIFI Responsable Technique Technical Manager

Pour déclarer, ou non, la conformité à la spécification, il ris pas été tenu explicitement compte de l'incertitude associée au nésultat Whether or not lo declare compliance with the specification, the uncertainty associated with the result was not explicitly taken into acc La reproduction de ce resport dessa intest subtrisée que sous sa forme intégrale Ripproduction of this test report is only permitted in let full form La CREPMI et peut être tenu responsable soit est information relatives à l'élément testé. Des informations sont fournée par le démands CREPMI cannot be held responsible for information relatives à très deserver. This information is provided by the applicant.

CEPRO



OLYMPUS WELDING BLANKET



Conforms to REGULATIONS (EC) No 1907/2006 (REACH) (EC No1272/2008[CLP/GHS], (EU) No content EU 2015/830.

Date of issue/Date of Revision 08/03/2022

0. INTRODUCTION

Continuous glass fiber products are articles under EU regulation (REACH&CLP), US regulation (TSCA) and Japanese Regulation and therefore, no MSDS is legally required. Cepro International BV decides to continue to provide our customers for assuring the safe handling and use of continuous glass fiber products. This MSDS was revised in accordance with GHS.

1. PRODUCTS AND COMPANY INFORMATION

Name of product CONTINUOUS GLASS FIBER FILAMENT

Product description Article

Other means of identification: HIGH SILICA GLASS FIBRE

HIGH SILICA GLASS FIBRE PLIED YARN HIGH SILICA GLASS FIBRE TEXTURED YARN HIGH SILICA GLASS FIBRE CHOPPED STRANDS

HIGH SILICA GLASS FIBRE FABRIC HIGH SILICA GLASS FIBRE MESH

HIGH SILICA GLASS FIBRE NEEDLED MAT

This material safety data sheet is valid for all these products.

Recommended use: Industrial applications

Manufacturer / Supplier Cepro International BV Date of issue March 2022

Provinciënbaan 16 5121 DL Rijen The Netherlands

Tel. no. for information / emergency +31 (0)161 22 64 72

2. HAZARD IDENTIFICATION

2.1 Classification of the substanceor mixture

Product definition: Article

Classificationaccording to Regulation (EC) No. 1272/2008[CLP/GHS] Not classified.

High silica glass fibre and high silica glass fibre articles are not classified as hazardous according to Regulation (EC) 1272/2008 as amended.

High silica glass fibre and high silica glass fibre articles does not contain any hazardous substances according to the RoHS - Directive 2017/2102/EU.

Details about chemical hazards are given in Section 3.

Toxicological aspects are developed in detail in Section 11.

2.2 Label elements

Signal word: No signal word

Hazard statements: No known significant effects or critical hazards

Precautionary statements

Prevention:
Response:
Storage:
Disposal:
Not applicable
Not applicable
Not applicable
Not applicable
Not applicable
Not applicable

OLYMPUS WELDING BLANKET

AnnexXVII - Restrictionson manufacture, placing on the market and use of certain dangerous substances, mixtures and articles:

Not applicable

Special packaging requirements

Containers tobe fitted with child-resistant fastenings Not applicable

Tactile warning of danger

2.3 Other hazards which do not result in

classification:

Notapplicable

Material is not an electrical conductor and may

OSH

accumulate static charge.

3. COMPOSITION / INFORMATION ON INGREDIENTS

Substance/mixture: Article

Product/ ingredient name	Identifiers	%	67/548/EEC R	fication legulation (EC) 2008[CPL]	Туре
Fibrous glass, continuous filament	Not available	> 99.8	Not classified	Not classified	[A]
Binder/Sizing	Not available	< 0.2	Not classified	Not classified	[C]

Type:

[A]Constituent

[B]Impurity

[C] Stabilisingadditive

Occupation exposure limits, if available, are listed in Section 8.

4. FIRST AID MEASURES

Description of first aid measures

Eye contact: Flush in running water (for at least 15 minutes) and consult if necessary a

doctor.

Inhalation: Remove from the scene of exposure to fresh air. If not breathing, if

breathing is irregular or if respiratory arrest occurs, provide artificial

respiration or oxygen by trained personnel.

Skin contact: Remove contaminated clothing and shoes. Wash copiously with lukewarm

soapy water without rubbing excessively. If irritation persists, seek medical

attention.

Ingestion: If swallowed, rinse mouth with water (only if the person is conscious).

Keep person warm and at rest. Do not induce vomiting. Get medical advice/

attention.

Protection of first-aiders: No action shall be taken involving any personal risk or without suitable

training.

5. FIRE-FIGHTING MEASURES

Suitable extinguishing agent: Any of the extinguishing agents, including water, carbon dioxide gas,

foam, dry chemicals and powder are effective. Select an extinguishing agent

depending on circumstances (source offire, etc.).

Suitable extinguishing method: Use any of the ordinary fire extinguishing methods.

Other information: High silica glass fibre and high silica glass fibre articles are not combustible.

Version 007 - Check our website for the latest version.

CEPRO_PFS_Weldingblankets_Premium_Olympus_2EN



OLYMPUS WELDING BLANKET



6. ACCIDENTAL RELEASE MEASURES

Personal precautions: Environmental precautions: Clean up Method: If necessary, wear a safety mask, safety gloves or safety goggles.

No special environmental precautions required.

If spilled on the floor, clean quietly so that dust particles will not be dispersed and put into a container or bag. For disposal, treat it same as general

industrial waste.

7. HANDLING AND STORAGE

7.1 Precautions for safe handling

Handling (Technical measures / Precautions / Safe handling advice):

It is preferable to avoid prolonged contact with the skin: wear gloves, garments with sleeves and long leggings or protective overalls, goggles and dust masks.

Storage:

Technical measures: Respect the stacking procedure recommended for

each type of product.

Storage conditions: Store away from excessive humidity to prevent damage to the product and to the packing materials, which could lead to storage

safety problems.

Incompatible material: Not relevant.

8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Occupational Exposure Limits:

Legal requirements for respirable and non-respirable dusts and fibres vary from country to country (or do not even exist). The table below (prepared using the knowledge we currently possess) shows the limits applicable indifferent countries for Time-Weighted Average (TWA) exposure.

Country	Dusts	WA (TimeWeighte- dAverage concentration) (mg/m3 for 8 hours work)	Fibres	WA (TimeWeightedAverage concentration) (Fibres/ml for 8 hours work)
Austria	fine	6	total	0.5
Belgium	total	10	No regulation	
Denmark	respirable total	5 10	total	1
Finland	total	10	total	1
France	total	10	respirable	1
Germany	respirable	3	respirable	0.25
Great Britain	respirable total	5 10	respirable	2
The Netherlands	respirable total	2 10	total	1
Ireland	respirable	5	respirable	2
Italy	respirable total	3 10	total	1



OLYMPUS WELDING BLANKET



Norway	respirable total	5 10	total	1
Portugal	total	4	total	1
Spain	total	10	total	1
Sweden	respirable total	5 10	total	1
Switzerland	total	6	respirable	0.5
USA	respirable total	5 (OSHA)* 15 (OSHA)*	total	1 (ACGIH)**
Japan	respirable total	2(JSOH)*** 8 (JSOH)***	total	3 (RPHDD)****

^{*} OSHA = Occupational Safety and Health Administration

Equipment measures: Install localized ventilation units in workplaces where dusts are generated by cutting, grinding and so on, and powder products such as milled fibers are handled. If ventilation units can't be installed for some reasons, be sure to wear a dust mask (approved by the government) during work. It is also preferable to provide facilities for washing the face and the body, gargling, changing and washing clothes.

Protective gear: Use the following protective gear as necessary in view of the conditions in the workplace environment.

- Respiratory protection: Dust mask (approved by the government authorities: replaceable / one-way)
- Hand protection: Gloves such as leather which don't allow glass fiber to pierce
- **Eyeprotection:** Safety glasses (goggle type)
- Skin and body protection: Loose-fitting top garment with long sleeves and collar (tightened cuffs) and long pants (tightened at the ankles).

9. PHYSICAL AND CHEMICAL PROPERTIES

9.1. High silicaglass fibre and high silica glass fibre articles:

Physical State: Solid

Form: Continuous or chopped or weaved or mats of fibre made up of

continuous, parallelfilaments holding together.

Colour: White or vellowish white

Odour: Odourless
Odour threshold: Not available
pH: Not applicable

Specific temperature at which changes in physical state occur: High silica glass fibre and high silica glass fibre articles:

Softening point: Littleton point (defined as the temperature for which the

viscosity of glass is 107.65 Poises): approximately 1250OC.

Melting point: Not applicable. Glass does not melt, but the viscosity decreases by elevation of temperature and is 103 for high silica glass in a range of temperature between 1650OC and 1750OC (fiberizing temperature).

Initial boiling point and boiling range: Not available.

Flash point: Not applicable. (Product does not sustain combustion)

Evaporationrate: Not available.

Material supports combustion: No.

Flammability (solid, gas): Not available.
Upper/lower flammability Not applicable.
or explosivelimits:

^{**} ACGIH = American Conference of Governmental Industrial Hygienists

^{***}JSOH = Japan Society for Occupational Health

^{****} RPHDD = Regulation on Prevention of Hazards Due and Dust of Japan



Relative density: 2.65 to 2.7

Solubility (-ies): Very low solubility in water. Sizes can be partially (and even totally)

dissolved in most organic solvents.

Partition coefficient: n-octanol/Water: Not available. **Auto-ignitiontemperature:** Not available.

Decomposition temperature: Only size products start to decompose at 200oC

Viscosity: Not applicable. Explosive properties: Not applicable. Oxidizing properties: Not applicable.

10. STABILITY AND REACTIVITY

10.1 High silica glass fibre and high silica glass fibre articles
Chemical Stability:

The products are stable.

Possibility of Hazardous reactions: Under normal conditions of storage and use, hazardous reactions will

not occur

Conditions to avoid: When exposed to high temperatures may produce hazardous decom-

position products. Refer to protective measures listed in sections 7 and 8.

Incompatible materials: None known.

Hazardous decomposition products: In continuous combustion conditions, in addition to water vapor and

CO2, small quantities of CO and NOx may be released from the combustion of the size. Other products may be released in limited quantities, depending on combustion conditions. This is why it is recommended to use high-temperature gas masks, when fighting

intense fires (see paragraph 5).

11. TOXICOLOGICAL INFORMATION

Acute toxicity:Not availableIrritation/Corrosion:Not availableSensitization:Not availableMutagenicity:Not available

Carcinogenicity: Not applicable. The International Agency for Research on Cancer

(IARC) classes glass fiber into category 3 (No classification exists

with regard to its carcinogenicity in humans.)

Reproductive Toxicity:
Teratogenicity:
Specific target organ toxicity (single
Not available.
Not available.

exposure):

Specific target organ toxicity (repeated Not available.

exposure):

Aspiration hazard: Not available.

Handling glass fibres:

When glass fibres are chopped, milled or sanded they are cut perpendicular to strand length and no smaller diameters filaments are generated. Conversely, significant quantities of dust can be generated, which is why it is recommended to use personal protection. In dusts, also present in some products (chopped strands, milled fibres), some studies have shown very low quantities of particles with fibrous aspects (I/d>3), short (but nevertheless longer than 5 μ m) and with an apparent diameter of under 3 μ m. Quantities measured in work atmospheres are 50 to 100 times lower than all the limits fixed for respirable fibres, but when there is a high risk of dust generation it is strongly recommended to wear masks.

12. ECOLOGICAL INFORMATION

Toxicity: Not available. Persistence and degradability: Not available. Bio accumulative potential: Not available.

Mobility in soil Soil/water partition Not available.

coefficient (KOC):

Mobility: Not available.



Results of PBT and vPvB assessment

PBT: No.

vPvB: Not available.

Other adverse effects: No known significant effects or critical hazards.

13. DISPOSAL CONSIDERATIONS

Waste treatment methods

High silica glass fibre and high silica glass fibre articles:

Depending on local regulations, glass fibre wastes can either be considered as **inert waste** or as **common industrial waste**. The generation of waste should be avoided or minimized wherever possible. Dispose of surplus and non-recyclable products via a licensed waste disposal contractor. As such they can be buried in landfills approved for these categories. Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.

Packaging:Clean cardboard, wood, plastic (film) and packaging can be eliminated in units specific to these products (i.e. for recycling or use as fuels).

14. TRANSPORT INFORMATION

	ADR/RID	AND	IMDG	IATA
UN number	Not regulated	Not regulated	Not regulated	Not regulated
UN proper shipping name	-	-	-	-
Transport Hazard class	-	-	-	-
Packing group	-	-	-	-
Environmental hazards	No.	No.	No.	No.
Marine pollutant substances	Not applicable.	Not applicable.	Not applicable.	Not applicable.
Additional information	None identified	None identified	None identified	None identified

Special precautions for user: Transport within user's premises - always transport in closed containers that are upright and secure.

15. REGULATORY INFORMATION

Continuous glass fiber is not classified as a "Dangerous Substance" or "Dangerous Preparation" according to EU-Directives 67/548/EEC, 1999/45/EC and amendments. Continuous glass fiber complies with all other national or local regulations regarding the use, transport, recycling, reuse, or disposal. Glass fiber is considered as an article and is exempted from requirements of TSCA, REACH, EINECS, DSL, AICS, KECL and so on.

Commercial 1/1 Certification 1/1 Safety 6/7 Technical Specifications 1/1



16. OTHER INFORMATION

This Material Safety Data Sheet is in addition to the Product Specification file and other technical documents issued by Cepro International BV, but does not replace them.

The information given by this document is based on the best knowledge at the moment. It is given in good faith. Furthermore, user attention is drawn to the possible risks run when the product is used for any purpose other than the one for which it was designed.

This MSDS does not exempt users from knowing and applying the rules regulating their activities. Users assume full responsibility for applying the appropriate safety measures when the product is used. For all additional information, users should contact their local Cepro International BV agent or the main supplier office at Cepro International BV.



OLYMPUS WELDING BLANKET



TECHNICAL DATA

Test			
1. Weave		12H Satin	
2. Selvage		Feathered (Feather length: 5-8 mm)	
3. Yarn, tex	warp	68 x 6 or 102x4	
	weft	68 x 6 or 102x4	
4. Width		900 mm	DIN EN 1773
5. Thickness*, mm		1,25 +/- 0,15	DIN EN ISO 5084
6. Weight, g/m²		1100, +70/-50	DIN EN 12127
7. Thread count per cm	warp	19 +/- 1	DIN 53853
	weft	11 +/- 1	
8. Tensile strength, min. N/2,5 cm	warp	2000	EN ISO 13934.1
	weft	1500	
9. Content of main components %		SiO2 96 +/- 1	Comp. Method
		Al2O3 3,5 +/- 0,5	PP - Q - K 05

Version 007 - Check our website for the latest version.