

PRODUCT INFORMATION

SIFMIG A15

BS: 2901 A15
EN ISO 636A: 2008 W2Ti
AWS A5.18: ER70S-2

DESCRIPTION

A triple deoxidised mild steel MIG wire for MAG welding unalloyed and low alloyed galvanised structural steels. The Titanium, Zirconium and Aluminium make this product ideal for welding oxidised rusted material and also coated plate (primed or painted). It is also often used in the welding of rimming and semi-killed steels.

WELDING POSITIONS



Suitable for use in the shipbuilding and offshore industry, general fabrication and construction, power generation, repair and maintenance and the transport and lifting industries.

TYPICAL WELD METAL COMPOSITION

C	0.1 %
Si	0.6 %
Mn	1.3 %
Al	0.2 %

TYPICAL MECHANICAL PROPERTIES

Melting Point	1450 °C
Ult Tensile Strength	440 N/mm ²
Hardness	120
Impact ISOVJ	80 @ -20 °C

MATERIAL TO BE WELDED

Suitable for use with CO₂ and Ar-CO₂ shielding gases. The wire is precision layer wound for positive uninterrupted feeding in semi-automatic and automated systems. Popular in welding mild steel and C-Mn steels used in the fabrication of tanks, pipework, machinery, tubular furniture, chassis and steel frames structures.

AVAILABLE FORMATS

SPOOLED WIRE (MIG / GMAW)			
Dia			15kg
0.8mm			WA150815
1.0mm			WA151015
1.2mm			WA151215

Shielding Gas:	Ar/ArCO ₂
----------------	----------------------

For further information, contact Weldability | Sif technical support on **0870 330 7757** or email service@weldability-sif.com



Registered in England No. 1684362
Registered Office: as above

Doc Ref: SIF/PI/WA150815